

# DURO LACK MC 50 SATINATA

**Two-component polyurethane lacquer with excellent chemical and physical characteristics**



## Description

DUROLACK MC 50 SATINATA is a two-component polyurethane, elastic, resilient and scratch-resistant lacquer. It covers very well and has an excellent yield; it has a very good resistance to washing with water and neutral detergents. Fully in conformity with 2004/42/CE. **Destinations:** Particularly suitable for varnishing all the different kinds of wooden floorings.

## Characteristics

Mixture ratio	1/1
Application temperature	+10°C ÷ +25°C
Application	roller 6 mm / brush
Thinning (if necessary)	DILUENTE DMC 50
Coverage	100 g/m <sup>2</sup>
Dust dry	1 h 30' <sup>(1)</sup>
Fingerprint dry	6 h <sup>(1)</sup>
Pot-Life	4 h <sup>(1)</sup>
Sandpapering	24 h <sup>(1)</sup>
Gloss level	75 gloss <sup>(2)</sup>
Chemical and physical characteristics	excellent
Coating	excellent
Storage stability	1 year <sup>(3)</sup>
Packaging	25 L (12,5+12,5) - 10 L (5+5) - 5 L (2,5+2,5)
Tool cleaning	DILUENTE DNE

- 1 at 20°C and 65% R.H.
- 2 onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days
- 3 in original sealed containers at temperatures between +10°C and +25°C

## How to use

After being mixed in the ratio above mentioned, DURO LACK MC 50 SATINATA has to be applied onto the wood flooring after having sanded, puttied and well vacuum cleaned it. Use first one or two coats of the two-component polyurethane (WR 306) and then one coat of DURO LACK MC 50 SATINATA to finish. The maintenance of wooden floors treated with DURO LACK MC 50 SATINATA has to be done with VELUREX range of products (see technical data sheets).

## Safety and risk information

Comp.A	<ul style="list-style-type: none"> <li>· FLAMMABLE.- REPEATED EXPOSURE MAY CAUSE SKIN DRYNESS OR CRACKING.- VAPOURS MAY CAUSE DROWSINESS AND DIZZINESS.-</li> <li>· EXTINGUISHING MEASURES: CO<sub>2</sub>, FOAM, AFFF, CHEMICAL POWDER FOR FLAMMABLE LIQUIDS.- IF SWALLOWED, SEEK MEDICAL ADVICE IMMEDIATELY AND SHOW THIS CONTAINER OR LABEL.</li> </ul>
Comp.B	<ul style="list-style-type: none"> <li>· FLAMMABLE.- HARMFUL BY INHALATION.- IRRITATING TO EYES.- MAY CAUSE SENSITIZATION BY INHALATION AND SKIN CONTACT.- REPEATED EXPOSURE MAY CAUSE SKIN DRYNESS OR CRACKING.</li> <li>· KEEP OUT OF THE REACH OF CHILDREN.- DO NOT BREATHE GAS, FUMES, VAPOUR, SPRAY.- AVOID CONTACT WITH SKIN.- WEAR SUITABLE GLOVES.- IN CASE OF ACCIDENT OR IF YOU FEEL UNWELL, SEEK MEDICAL ADVICE IMMEDIATELY (SHOW THE LABEL WHERE POSSIBLE).- IN CASE OF ACCIDENT BY INHALATION: REMOVE CASUALTY TO FRESH AIR AND KEEP AT REST.</li> </ul> <p>Contents:ALIPHATIC POLYISOCYANATE ; M-TOLYLIDENE DIISOCYANATE ;</p>

## Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



[http://www.chimiver.com/tds/EN\\_DURO\\_LACK\\_MC\\_50\\_SATINATA.pdf](http://www.chimiver.com/tds/EN_DURO_LACK_MC_50_SATINATA.pdf)