

Technical Datasheet

Item Code: PRYA000X | Rev.: 2018-03-06 | Ver: 3.0

PRYMER A

Single-component water-based antidust primer



Description

PRYMER A is a single-component water-based primer based on a nano-dispersion of resins with guarantee high penetration even in low absorption subfloors. PRYMER A is recommended as antidust treatment and superficial consolidation of absorbent subfloors, cementitious and anhydrite self-levellers. It is also suitable for heated subfloors. The subsequent gluing has to be done with reactive glues. **Destinations:** anti-dusting, superficial consolidation for indoor use.

Characteristics

Mixture ratio	single-component
Application temperature	+10°C ÷ +25°C
Application	roller 8 mm / brush
Thinning (if necessary)	water
Coverage	100 g/m ²
Total drying time	3-4 h (depending on the quantity applied and subfloor absorption) ⁽¹⁾
Storage stability	1 year ⁽²⁾
Packaging	10 kg
Tool cleaning	water (with fresh primer)

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

Consolidation of anti-dust subfloor

It is essential to make sure that there is not a rising damp from the substrate. The subfloor to be treated has to be clean, free of any contaminant. Apply by roller PRYMER A evenly without any excess, after the complete drying proceed with the subsequent gluing of the wooden floors using: ADESIVER 501 EP, ADESIVER HERCULES, SIGOL, ADESIVER 327 PU, ADESIVER RE 702, UNISIL, ELASTIC (see technical data sheet).

Warnings

Protect from frost during transit and storage. Avoid prolonged exposure to temperatures below 0°C.

Label elements

· Safety data sheet available on request. Contains MIXTURE OF: 5-CHLORO-2-METHYL-2H-ISOTHIAZOL-3-ONE; 2-METHYL-2H-ISOTHIAZOL-3-ONE (3: 1), 1,2-BENZISOTHIAZOL-3 (2 H) -ONE. May produce an allergic reaction.

Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_PRYMER_A.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.